



RINKO

& ASSOCIATES, LLC / WWW.RINKOLABS.COM

Advanced Analytical Chemistry & Materials Engineering

January 7, 2014

Fellert Acoustical Ceilings AB
Krykangsgatan 6
503 38 BORAS
Sweden

Attn: Mr. Michael Rosenberg

Ref: Lab File # RA-1211-1A-B-14C1

1. SAMPLE(S):

One (1) miscellaneous sample;

One (1) 125 ml. container of Even Better Acoustical Coating Natural White

2. ANALYSIS PERFORMED:

Even Better Acoustical Coating Natural White

Determination of Volatile Organic Compound (VOC) Content of Paints and Related Coatings – **ASTM D3960**

3.RESULTS:

**Determination of Volatile Organic Compound (VOC) Content of Paints and Related Coatings –
ASTM D3960**

Sample: Even Better Acoustical Coating Natural White

	Density (g/ml)	Total Volatile Content (% w/w)*	Total Water Content (% w/w)*	VOC	
				lbs/gal	g/litre
	1. 1.3106	60.37	60.32	0.02	3
	2. 1.3106	60.37	60.32	0.02	3
AVG	1.3106	60.37	60.32	0.02	3



Robert A. Haffner
Chief Analytical Chemist/Engineer