



RINKO

& ASSOCIATES, LLC / WWW.RINKOLABS.COM

Advanced Analytical Chemistry & Materials Engineering

November 6, 2014

Fellert Acoustical Ceilings AB
Krykangsgatan 6
503 38 BORAS
Sweden

Attn: Mr. Michael Rosenberg

Ref: Lab File # RA-1106-1A-B-14

1. SAMPLE(S):

Two (2) sealed 500 ml containers of adhesives;
Even Better Board Adhesive.


2. ANALYSIS PERFORMED:

Volatile Organic Compound (VOC) Content using EPA Method 24

3. RESULTS:

Volatile Organic Compound (VOC) Content using EPA Method 24

Density (g/ml)	Total Volatile Content (% w/w)*	Total Water Content (% w/w)*	VOC	
			lbs/gal	g/litre
1. 1.2811	35.43	35.33	0.02	2
2. 1.2811	35.43	35.33	0.02	2
AVG 1.2811	35.43	35.33	0.02	2


Robert A. Haffner,
Chief Analytical Chemist/Engineer