



**RINKO**

& ASSOCIATES, LLC / [WWW.RINKOLABS.COM](http://WWW.RINKOLABS.COM)

**Advanced Analytical Chemistry & Materials Engineering**

March 28, 2014

Fellert Acoustical Ceilings AB  
Krykangsgatan 6  
503 38 BORAS  
Sweden

Attn: Mr. Michael Rosenberg

Ref Lab File#RA-0327-1A-14R

**1. SAMPLE(S):**

One (1) litre of Alcro TAT Grundfarg vatrum – Light Green

**2. ANALYSIS PERFORMED:**


Volatile Organic Compound (VOC) Content using EPA Method 24

### 3. RESULTS:

Volatile Organic Compound (VOC) Content using EPA Method 24

Sample: Alcro TAT Grundfarg vatrum – Light Green

Density (g/ml)	Total Volatile Content % (w/w)	Total Water Content % (w/w)	VOC	
			<u>g/litre</u>	<u>lbs/gal</u>
a. 1.2643	36.36	35.36	23	0.19
b. 1.2643	36.38	35.38	23	0.19
AVG 1.2643	<u>36.37</u>	<u>35.37</u>	<u>23</u>	<u>0.19</u>



Robert A. Haffner,  
Chief Analytical Chemist/Engineer