



RINKO

& ASSOCIATES, LLC / WWW.RINKOLABS.COM

Advanced Analytical Chemistry & Materials Engineering

January 7, 2014

Fellert Acoustical Ceilings AB
Krykangsgatan 6
503 38 BORAS
Sweden

Attn: Mr. Michael Rosenberg

Ref: Lab File # RA-1211-1A-B-14B1A

1. SAMPLE(S):

One (1) miscellaneous sample;

a) One (1) 8" x 11" x 1" section of Acoustical Plaster- Fellert Even Better

2. ANALYSIS PERFORMED:

Acoustical Plaster- Fellert Even Better

A. Test Method for Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber -**ASTM D3273** and Test Method for Evaluating Degree of Surface Disfigurement of Paint Films by Microbial(Fungal or Algal) Growth or Soil

and Dirt Accumulation- **ASTM D3274**


3.RESULTS:

A. Acoustical Plaster- Fellert Even Better

ASTM D3273/ ASTM D3274

a).	<u>Panel #</u>	<u>Exposure Time</u>			
		<u>1 week</u>	<u>2 weeks</u>	<u>3 weeks</u>	<u>4 weeks</u>
	1.	10 ²	10	10	10
	2.	10	10	10	10
	3.	10	10	10	10

²Numbers are given as a Disfigurement Rating , where 10 = no growth of Fungus or Algae present.



Robert A. Haffner,
Chief Analytical Chemist/Engineer