



RINKO

& ASSOCIATES, LLC / WWW.RINKOLABS.COM

Advanced Analytical Chemistry & Materials Engineering

May 23, 2014

Fellert Acoustical Ceilings AB
Krykangsgatan 6
503 38 BORAS
Sweden

Attn: Mr. Michael Rosenberg

Ref: Lab File # RA-0516-2A-C-14A

1. SAMPLE(S):

One (1) miscellaneous sample;

A. Dry Powder Plaster- total of one (1) bag of plaster

Fellert Even Better

2. ANALYSIS PERFORMED:

Determination of Volatile Organic Compound (VOC) Content of Paints and Related Coatings – ASTM D3960

3. RESULTS:


Determination of Volatile Organic Compound (VOC) Content of Paints and Related Coatings – ASTM D3960

Sample: Fellert Even Better

Density (g/ml)	Total Volatile Content (% w/w)*	Total Water Content (% w/w)*	VOC ¹	
			lbs/gal	g/litre
1. 0.9730	97.08	97.06	0.03	4
2. 0.9730	97.08	97.06	0.03	4
AVG 0.9730	97.08	97.06	0.03	4

* Numbers reported are based on percentage (by wt.)

¹VOC was measured by mixing 9.0 gallons of water to 5 kg of Fellert Even Better



Robert A. Haffner,
Chief Analytical Chemist/Engineer