



**RINKO**

& ASSOCIATES, LLC / [WWW.RINKOLABS.COM](http://WWW.RINKOLABS.COM)

**Advanced Analytical Chemistry & Materials Engineering**

May 10, 2012

Fellert North America  
3411 Brinkerhoff Road  
Kansas City, KS 66115

Attn: Mr. Sandy Andrew

Ref: Lab File # RA-0411-1A-F-12D

**1. SAMPLE(S):**

Three (3) miscellaneous samples;

A. Plaster- total of one (1) bag of plaster

1. Product Name: Fellert Even Better

B. Acoustical Ceiling Tiles- Total of two (2)

1. Product Name: Fellert Even Better

**2. ANALYSIS PERFORMED:**

B. Acoustical Ceiling Tiles:

2. Test Method for Compressive Strength of Sprayed Fire-Resistive  
Material(SFRM)applied to Structural Members- **ASTM E761-92**


### 3. RESULTS:

#### B. Acoustical Ceiling Tiles

#### 2. Test Method for Compressive Strength of Sprayed Fire-Resistive Material(SFRM)applied to Structural Members- ASTM E761-92

Sample : Fellert Even Better

ASTM E761-92		ASTM E605-93
<u>Compressive Strength (psi)</u>		<u>Density (lbs/ft<sup>2</sup>)</u>
1.	160	1.86
2.	160	1.86
3.	160	1.86
<b>Average</b>	<hr/> 160	<hr/> 1.86



Robert A. Haffner,  
Chief Analytical Chemist/Engineer