



RINKO

& ASSOCIATES, LLC / WWW.RINKOLABS.COM

Advanced Analytical Chemistry & Materials Engineering

May 4, 2017

Fellert Acoustical Ceilings AB
Krykangsgatan 6
503 38 BORAS
Sweden

Attn: Mr. Michael Rosenberg

Ref: Lab File # RA-0502-1A-C-17C

1. SAMPLE(S):

One (1) sealed, 500 ml container of Even Better Board Adhesive

2. ANALYSIS PERFORMED:

Volatile Organic Compound (VOC) Content using EPA Method 24

3. RESULTS:

Volatile Organic Compound (VOC) Content using EPA Method 24

Sample: Even Better Board Adhesive

	Density	Total Volatile Content	Total Water Content	VOC	
	(g/ml)	(% w/w)*	(% w/w)*	lbs/gal	g/litre
1.	1.1114	16.92	16.82	0.01	1
2.	1.1114	16.90	16.80	0.01	1
AVG	1.1114	16.91	16.81	0.01	1

Robert A. Haffner,
Chief Analytical Chemist/Engineer

1961 E. Green Springs Rd. • Rescue, CA 95672
Tel (805)545-0105 Fax (530)698-6368
General Inquiries: info@rinkolabs.com
Robert Haffner Lab Director: Rh4rinko@yahoo.com