



RINKO

& ASSOCIATES, LLC / WWW.RINKOLABS.COM

Advanced Analytical Chemistry & Materials Engineering

May 4, 2017

Fellert Acoustical Ceilings AB
Krykangsgatan 6
503 38 BORAS
Sweden

Attn: Mr. Michael Rosenberg

Ref: Lab File # RA-0502-1A-C-17A

1. SAMPLE(S):

One (1) sealed, 500 ml container of Even Better Acoustical Coating

2. ANALYSIS PERFORMED:

Determination of Volatile Organic Compound (VOC) of Paints and Related Coatings-
ASTM D3960

3. RESULTS:

Determination of Volatile Organic Compound (VOC) of Paints and Related Coatings-
ASTM D3960

Sample: Even Better Acoustical Coating

	Density (g/ml)	Total Volatile Content (% w/w)*	Total Water Content (% w/w)*	VOC	
				lbs/gal	g/litre
1.	1.2392	58.99	58.94	0.02	2
2.	1.2392	58.96	58.92	0.02	2
AVG	1.2392	58.98	58.93	0.02	2

Robert A. Haffner,
Chief Analytical Chemist/Engineer